



DOWSIL™ PV-8303 Ultra Fast Cure Sealant

Ultra fast cure silicone adhesive sealant

Features & Benefits

- Adhesion to typical PV substrates such as glass, aluminum and common backsheet materials
- Resistant to hot and humid conditions once cured
- Good water and UV resistance
- Ultra fast cure for fully automated processes
- Multiple UL ratings

Composition

- Two-part, ultra fast cure silicone sealant

Applications

- Used as rail bonding, frame sealing, and junction box bonding on photovoltaic modules

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
DOWSIL™ PV-8303 Ultra Fast Catalyst Black		
Color		Black
Viscosity	mPa s or cP	350,000
Specific gravity		1.03
DOWSIL™ PV-8300 Base		
Color		White
Extrusion rate	Grams/ m	190
Specific gravity		1.31
DOWSIL™ PV-8300 Base with DOWSIL™ PV-8303 UF Catalyst		
Color		Black
Skin over time	minutes	8-10 range
Snap time (working time)	minutes	8-10 range
Cure time @ 25°C	hours	2.5
Specific gravity		1.31

Typical Properties (Cont.)

Property	Unit	Result
Properties after full cure – 7 days at RT – measured on 2 mm cured sheets		
Durometer hardness	Shore A	38 – 44
Tensile strength (H-Bar Test) ¹	Psi	174
	MPa	1.2
Elongation to break (H-Bar Test) ¹	%	80
Tensile strength (Sheet material test) ²	Psi	300 – 350
	MPa	2.1 – 2.4
Elongation to break (Sheet material test) ²	%	220
Adhesion via Peel Test – 7 day cure at 23°C		
Cohesive Failure	%	100
PPO, Anodized Al, Glass and Tedlar	Pli	15 – 24
UL Ratings		
UL 94	Flammability	HB
UL 746A	HWI	2
	HAI	3
	CTI	0
UL 746B	RTI	105°C (221°F)

¹Test per external reference NFP 85-405, DTU 39.4.

²Test per external reference ASTM D 412 (ASTM: American Society for Testing and Materials.)

Description

DOWSIL™ PV-8303 Ultra Fast Cure Sealant is designed to offer long-term bonding and protection against moisture, environmental degradation, mechanical and thermal shock where ultra fast cure is needed for automated processing. DOWSIL™ PV-8303 Ultra Fast Cure Sealant shows good adhesive resistance to hot and humid conditions.

How To Use

Substrate Preparation

All surfaces must be clean and dry. Degrease and wash off any contaminants that could impair adhesion.

Mixing

DOWSIL™ PV-8303 Ultra Fast Cure Catalyst is designed to be used with DOWSIL™ PV-8300 Base in a mix ratio of 100 parts base to 14 parts catalyst by weight. Suitable meter/mix equipment should be equipped with gear or piston metering pumps for base and catalyst, and a static mixer.

Curing Conditions

DOWSIL™ PV-8303 Ultra Fast Cure Sealant achieves a skin over time of 8 to 10 minutes at 25°C and develops adhesion rapidly to metals, glass and plastic substrates. Adhesion is achieved to most substrates without the use of primer, or of surface activation methods.

Clean Up

Extra product can be wiped up with a clean cloth before curing. If the product is cured, mechanical removal can be used to scrape off the substrate.

**Handling
Precautions**

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Attention: When the information contained in the PSDS relates to a prototype material or a research and development sample, please be aware that hazard evaluation and handling recommendations are based on preliminary test data (if available), professional judgment in comparison with materials of a similar composition or a combination of these sources, as appropriate. For further information, please consult Dow's Health, Environmental and Regulatory Affairs Department (see Health and Environmental Information section).

**Usable Life and
Storage**

When stored at or below 25°C (77°F) in the original unopened containers DOWSIL™ PV-8303 Ultra Fast Cure Catalyst has a usable life of 12 months and DOWSIL™ PV-8300 Base has a usable life of 14 months from the date of manufacture.

**Packaging
Information**

DOWSIL™ PV-8303 Ultra Fast Cure Catalyst and DOWSIL™ PV-8300 Base are available in standard pail and drum packaging. Detailed container size information may be obtained from your Dow representative.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

**Health and
Environmental
Information**

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, dow.com or consult your local Dow representative.

**Disposal
Considerations**

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

**Product
Stewardship**

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

dow.com

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

