



ZINC

Reference : 10390

1. General description

Long term cathodic corrosion protection. Withstands scratching, bending and spot welding. Meets EN ISO 1461:1999 as a suitable renovation media.



2. Features

- Excellent touch-up for galvanised surfaces.
- Long term corrosion protection.
- Excellent corrosion resistance through cathodic protection, even when the coating is damaged.
- Can be painted over by most of the commonly used finishes.
- No chlorinated solvents.
- Totally free of lead and chromates.
- High temperature resistance.

3. Applications

- Cleaning mechanical parts.
- Handling equipment.
- Railroad equipment.
- Agricultural equipment.
- Long term outdoor corrosion protection.
- Corrosion protection of all ferrous materials.

4. Directions



Manufactured by :
CRC Industries Europe bvba
 Touwslagerstraat 1
 9240 Zele Belgium
 Tél.: (32)(0) 52/45.60.11 Fax : (32)(0) 52/45.00.34
www.crcind.com





ZINC

Reference : 10390

- Shake well before use.
- Shake until the agitator ball moves freely in the can.
- Remove most of the loose dirt with a wire brush.
- Best results are obtained with 2 lighter rather than 1 heavy coat. Additional coats can be applied after 10 - 15 minutes.
- A minimum film thickness of 40 μ is needed for adequate protection.
- Do not use on energized equipment.
- Do not use on sensitive electronic equipment.
- Clean the aerosol valve by turning the can upside down and spraying until only propellant escapes.
- **A safety data sheet (MSDS) according to EC Regulation N° 1907/2006 Art.31 and amendments is available for all CRC products.**

5. Typical product data (without propellant)

	Aerosol	Bulk
Appearance	Liquid	Liquid
Color	grey	grey
Odour	Characteristic odor	solvent
Density	1.431 g/cm ³ (@ 20°C)	2.2 g/cm ³ (@ 20°C)
Flash Point	< 0 °C	39 °C (Closed Cup)
Operating temperature active product	-30 --> +200 °C	-30 --> +200 °C
Drying time active product	40 min	40 min
salt spray resistance active product	350 h	350 h
Typical coat weight	40 μ	40 μ
Flexibility of dry coating	OK 6 mm mandrel	OK 6 mm mandrel
Adhesion on steel dry coating	0/1 GT	0/1 GT

6. Packaging

Aerosol	12x400 ML
	12x500 ML
Bulk	4x750 ML

7. Remarks

Typical corrosion protection results will depend mainly on surface conditions and environment. It may be several months up to over 1 year outdoors or more than 2 years indoors. The first application should be checked periodically for signs of corrosion. Once the time of protection under any specific condition is determined, CRC Zinc may be re-applied at intervals to maintain protection.



Manufactured by :
CRC Industries Europe bvba
Touwslagerstraat 1
9240 Zele Belgium
Tél.: (32)(0) 52/45.60.11 Fax : (32)(0) 52/45.00.34
www.crcind.com



**ZINC**

Reference : 10390

All statements in this publication are based on service experience and/or laboratory testing. Because of the wide variety of equipment, conditions of use and the unpredictable human factors involved, we recommend that our products are tested on-the-job prior to use. All information is given in good faith but without warranty neither expressed nor implied. This Technical Data Sheet may already have been revised as a result of a change in legislation, availability of components or newly acquired experiences. The latest and only valid version of this Technical Data Sheet will be sent to you upon simple request or can be found on our website: www.crcind.com We recommend that you register on our website for this product, thus enabling you to automatically receive any future updates.

Version CRC_GREEN-ZINC-20090619

Date 19/06/2009



Manufactured by :
CRC Industries Europe bvba
Touwslagerstraat 1
9240 Zele Belgium
Tél.: (32)(0) 52/45.60.11 Fax : (32)(0) 52/45.00.34
www.crcind.com

