



Körapur 784

General Properties	Technology/Base	Polyurethane (PU)
	Type of Product	Adhesive
	Curing	Polyaddition curing
	Mechanical Properties	Structural
	Parts	Two part system
	Part A (Resin)	Körapur 784
	Part B (Hardener)	Köracur TH 715 Köracur TH 717
	Product Benefits	Several potlives available High mechanical properties Flexible use in various applications No significant shrinkage

Typical Technical Data

Part A Körapur 784

Physical Properties		
Density	1.2 g/cm ³	DIN EN 542
Colour	black	
Processing Guidelines and Parameters		
Storage Temperature	15 °C to 25 °C	
Viscosity	40,000 mPa·s	Kö-test method 100000

Part B Köracur TH 715

Physical Properties		
Density	1.6 g/cm ³	DIN EN 542
NCO content	14%	
Colour	white	
Processing Guidelines and Parameters		
Storage Temperature	15 °C to 25 °C	
Viscosity	32,000 mPa·s	Kö-test method 100000

Part B Köracur TH 717

Physical Properties		
Density	1.6 g/cm ³	DIN EN 542
NCO content	14%	
Colour	beige	
Processing Guidelines and Parameters		
Storage Temperature	15 °C to 25 °C	
Viscosity	25,500 mPa·s	Kö-test method 100000



General

Physical Properties		
Colour	anthracite	Köracur TH 715
Colour	black	Köracur TH 717
Processing Guidelines and Parameters		
Mixing Ratio (Part A : Part B) by Weight	1 : 1.3	
Mixing Ratio (Part A : Part B) by Volume	1 : 1	
Processing Temperature	15 °C to 25 °C	
Curing		
Potlife	1 min, 3 min, 5 min	Kö-test method 100172
Cured Material Characteristics		
Shore Hardness (Type D)	75	DIN EN ISO 868
Lap Shear Strength	15 MPa	DIN EN 1465, substrates: aluminium/aluminium
Service Conditions		
Service Temperature	-160 °C to 90 °C	
Short-term temperature resistance	120 °C	min. 60 min

Product Properties

Applications	Fields of Application	Automotive Construction Industrial assembly Transportation
	Typical Applications	Bonding of parts of bodywork, such as side panels, wheel houses and door sheets Assembly and repair
Processing	Suitable Substrates	PVC-U (rigid) Various aluminium alloys Various steel alloys Various composite materials (e.g. CFRP, GFRP)
	Consistency	Non-sagging Pasty
	Surface Requirements	Dry Clean Free of grease Free of dust
	Application Method	Using side-by-side cartridge with static mixer
	Application Equipment	Two part mixing and metering system
	Product is free of	Solvents
Cleaning	Cleaner for Tools	Körasolv PU
Hints	Moisture Sensitivity	The adhesive must not be exposed to moisture before and during application. Moisture causes foaming leading to lower mechanical properties.



Interested in More Product Options? - Just Get Our App



Automotive Interiors All Regions



Mobile Homes EIMEA

Additional Information

Storage

Körapur 784 should be used within the shelf life specified on the packaging. The storage stability applies to material stored under appropriate conditions only (original unopened containers, recommended storage temperature).

Processing

Refer to the technical data table regarding processing parameters. Low temperatures can cause a temporary increase in viscosity resulting in reduced extrusion and slower curing rates.

Safety

Please read our Safety Data Sheet (SDS) and the labels of each product before use. The valid safety regulations must be considered.

Cleaning

Clean tools immediately after use. Once cured, the material can only be removed mechanically. Appropriate cleaners are listed in the product properties table. For further information please contact your local sales office.

Preparation

For some substrates the use of mechanical pre-treatment and/or cleaner or primer is necessary to achieve good adhesion. Refer to the product properties section of this data sheet for special surface requirements and suitable adhesion promoters.

Disposal

Please refer to the Safety Data Sheet (SDS) for appropriate disposal instructions.

IMPORTANT: Information, specifications, procedures and recommendations provided (information) are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is users sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the users intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) **the total aggregate liability of H.B. Fuller** for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, **is limited to replacement of affected products or refund of the purchase price for affected products.** (2) H.B. Fuller shall not be liable for **loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses** arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fullers liability for fraud, gross negligence or for death or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.

