



Körapur 128 S

| | | |
|---------------------------|-----------------------|---|
| General Properties | Technology/Base | Polyurethane (PU) |
| | Type of Product | Sealant |
| | Curing | Moisture curing |
| | Mechanical Properties | Elastic |
| | Parts | One part system |
| | Colour | White |
| | Product Benefits | Self-levelling High cold resistance High heat resistance Excellent moisture resistance Excellent weather resistance |

Typical Technical Data

General

| | | |
|---|-----------------------|--|
| Physical Properties | | |
| Density | 1.2 g/cm ³ | DIN EN ISO 2811-1 |
| Glass Transition Temperature | -54 °C | DIN EN ISO 6721-1 |
| Processing Guidelines and Parameters | | |
| Storage Temperature | 5 °C to 25 °C | |
| Processing Temperature | 15 °C to 35 °C | |
| Curing | | |
| Skin Formation Time | 30 min | Kö-test method 100109, Climate according to DIN 50014 |
| Curing to Depth | 3 mm/d | within first 24 h; Climate according to DIN 50014 |
| Change in Volume | < -1% | DIN EN ISO 10563 |
| Cured Material Characteristics | | |
| Shore Hardness (Type A) | 40 | DIN ISO 7619-1, after 28 d; thickness of specimen = 6 mm |
| Tensile Strength | 1.5 MPa | DIN EN ISO 527 |
| Elongation at Break | 500% | DIN EN ISO 527 |
| Tear Strength | 5 N/mm | DIN ISO 34-1 Type B |
| Service Conditions | | |
| Service Temperature | -40 °C to 90 °C | |
| Short-term temperature resistance | 120 °C | 60 min |



Product Properties

| | | |
|---------------------|---|--|
| Applications | Fields of Application | Automotive Construction Industrial assembly Transportation |
| Processing | Suitable Substrates | Painted or powder coated surfaces Various galvanized steels Various aluminium alloys Various steel alloys Duroplastics Wood |
| | Surface Requirements | Dry Clean Free of grease |
| | Surface Cleaning | Körasolv PU Körasolv WL |
| | Adhesion Promoter (absorbing surface) | Körabond HG 74 E |
| | Adhesion Promoter (non absorbing surface) | Körabond HG 81 |
| | Application Method | Pouring |
| | Application Equipment | Sachet dispenser Dispensing system |
| | Product Overpaintability | After skin formation (depending on paint) |
| Cleaning | Cleaner for Tools | Körasolv PU |
| Hints | Resistance against UV Radiation | Not suitable for glass bonding with permanent UV radiation to the bonding area. Please ask your local sales office for products suitable for such applications. |
| | Stress Cracking | Preliminary tests must be carried out on plastics with a tendency to stress cracking. (PMMA, ABS, PC or PS) |
| | Compatibility with Polystyrene Foams | Not suitable for bonding polystyrene foams. Please ask your local sales office for products suitable for such applications. |
| | Avoid Contact with Isocyanate Reactive Substances | Avoid direct contact with isocyanate reactive substances, especially alcohol such as spirit, dilutions, cleaning compounds and fission products of silane-modified polymers or silicones until the adhesive has attained full cure. This will prevent the adhesive from curing properly. |

Interested in More Product Options? - Just Get Our App



Trailer EIMEA



Additional Information

Storage

Körapur 128 S should be used within the shelf life specified on the packaging. The storage stability applies to material stored under appropriate conditions only (original unopened containers, recommended storage temperature).

Safety

Please read our Safety Data Sheet (SDS) and the labels of each product before use. The valid safety regulations must be considered.

Preparation

For some substrates the use of mechanical pre-treatment and/or cleaner or primer is necessary to achieve good adhesion. Refer to the product properties section of this data sheet for special surface requirements and suitable adhesion promoters.

Processing

Refer to the technical data table regarding processing parameters. Low temperatures can cause a temporary increase in viscosity resulting in reduced extrusion and slower curing rates.

Cleaning

Clean tools immediately after use. Once cured, the material can only be removed mechanically. Appropriate cleaners are listed in the product properties table. For further information please contact your local sales office.

Disposal

Please refer to the Safety Data Sheet (SDS) for appropriate disposal instructions.

IMPORTANT: Information, specifications, procedures and recommendations provided (information) are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is users sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the users intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) **the total aggregate liability of H.B. Fuller** for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, **is limited to replacement of affected products or refund of the purchase price for affected products.** (2) H.B. Fuller **shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses** arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fullers liability for fraud, gross negligence or for death or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.